

Properties: Medium **Shore A hardness after 24 hrs:** **Approx. 45**

Max. work time (including mix time):	2.25 minutes
Removal time from mouth:	6.5 minutes

Properties: Universal **Shore A hardness after 24 hrs:** **Approx. 65**

Max. work time (including mix time):	2.25 minutes
Removal time from mouth:	6.5 minutes

Properties: Heavy **Shore A hardness after 24 hrs:** **Approx. 55**

Max. work time (including mix time):	2.25 minutes
Removal time from mouth:	6.5 minutes

Properties: Bite **Shore A hardness after 24 hrs:** **Approx. 75**

Max. work time (including mix time):	1.6 minutes
Removal time from mouth:	5.0 minutes

Properties: NO-FLEX **Shore A hardness after 24 hrs:** **Approx. 80**

Max. work time (including mix time):	1.6 minutes
Removal time from mouth:	5.0 minutes